

U.S. Patent Application Serial No. 09/824,803  
Amendment dated September 10, 2003  
Reply to OA of **June 10, 2003**

**IN THE CLAIMS:**

Please add new claim 8 as follows:

1. (Previously Presented): A method of producing a continuous sheet having optical functions comprising the steps of:

extruding a melted thermoplastic resin between a continuous release sheet having a three-dimensional pattern having optical functions on its surface and any one selected from a cooling roll with a mirror surface, a cooling roll with an uneven pattern, another continuous release sheet having a three-dimensional pattern or other continuous sheet having optical functions which has a three-dimensional pattern or does not have a three-dimensional pattern,

transferring the three-dimensional pattern of said continuous release sheet or mirror surface or uneven pattern of the cooling roll or the three-dimensional pattern of said another continuous release sheet or the other continuous sheet on a surface of the thermoplastic resin or simultaneously transferring and laminating the other continuous sheet, and

cooling and removing the continuous release sheet, wherein

the continuous release sheet comprises a curable resin on which said three-dimensional pattern having the optical functions is formed before said extruding step, and a change in a surface-gloss of a layer, on which the three-dimensional pattern is formed, of the continuous release sheet is not more than 30% in pressing a hot plate heated to 160°C under a force of 20 kg/cm<sup>2</sup> for 3 seconds and the release sheet may be wound in a form of cylinder of not more than 12 inches in diameter.

2. (Previously Presented): A method for producing a continuous sheet having optical functions comprising the steps of:

extruding a melted thermoplastic resin between a continuous release sheet having a three-dimensional pattern having optical functions on its surface and any one selected from a cooling roll with a mirror surface, a cooling roll with an uneven pattern, another continuous release sheet having a three-dimensional pattern or other continuous sheet having optical functions which has a three-dimensional pattern or does not have a three-dimensional pattern,

transferring the three-dimensional pattern of said continuous release sheet or mirror surface or uneven pattern of the cooling roll or the three-dimensional pattern of said another continuous release sheet or the other continuous sheet on a surface of the thermoplastic resin or simultaneously transferring and laminating the other continuous sheet, and

cooling and removing the continuous release sheet, wherein

the continuous release sheet comprises a composite release sheet composed of a curable resin on which said three-dimensional pattern having the optical functions is formed before said extruding step, and a substrate and a change in a surface-gloss of a layer, on which the three-dimensional pattern is formed, of the composite release sheet is not more than 30% in pressing a hot plate heated to 160°C under a force of 20kg/cm<sup>2</sup> for 3 seconds and the release sheet may be wound in a form of cylinder of not more than 12 inches in diameter.

3. (Original): A method for producing a continuous sheet having optical functions as set forth in claim 1 or 2, wherein the other sheet to be simultaneously transferred and laminated is a

light-transmitting base sheet or an optical function base sheet.

4. (Original): A method for producing a continuous sheet having optical functions as set forth in claim 1 or 2, wherein the three-dimensional pattern of the continuous release sheet having optical functions is formed by a metallic embossing roll or a thermoplastic sheet on which a pattern is formed by extruding a melted thermoplastic resin on a metallic embossing roll.

5. (Original): A method for producing a continuous sheet having optical functions as set forth in claim 1 or 2, wherein the curable resin is a light-curable resin.

6. (Original): A method for producing a continuous sheet having optical functions as set forth in claim 1 or 2, wherein a ratio of the thickness of the layer on which a three-dimensional pattern of the composite release sheet having the optical functions to that of the substrate is 1/10 to 2/1.

7. (Original): A method for producing a continuous sheet having optical functions as set forth in claim 2, wherein the substrate of the composite release sheet is a sheet of a biaxially orientated polyethylene terephthalate.

8. (New): A method for producing a continuous sheet having optical functions as set forth in claim 1 or 2, wherein the curable resin is selected from a polymerizable acrylic prepolymer

U.S. Patent Application Serial No. **09/824,803**

Amendment dated September 10, 2003

Reply to OA of **June 10, 2003**

containing, as a skeleton, polyester, polyurethane, epoxy and polyether and having an acryloyl group as a functional group.